



British Steel is constantly working to develop new grades of steel with enhanced properties to meet the most stringent quality requirements.

We produce high-strength steel to meet the demands of the global tyre industry striving to manufacture lighter and more durable tyres and improve fuel economy and vehicle performance.

Our focus on customer specifications

Our tyre reinforcement cord is manufactured to meet individual customer specifications. Tensile strength is altered by adapting the steel microstructure, while scale characteristics can be tailored to suit each customer's preferred descaling method. This ensures we deliver a steel solution that meets your exact needs, drawing on our application knowledge and material development expertise.

Rigorous testing for quality assurance

The quality of our products is assured by rigorous testing procedures conducted in well-equipped laboratories to verify stringent criteria such as segregation, steel cleanliness, scale, surface quality, decarburisation, chemical composition, size, shape and tensile strength properties. Our products meet the required standards for the most challenging and safety-critical applications.

British Steel is accredited to IATF 16949:2016 the internationally-adopted quality management system standard for the automotive industry, ISO 9001:2015 for our quality management system and ISO 14001:2015 for our environmental management system.

Delivering quality

Our streamlined dispatch facilities allow us to offer an efficient delivery service. The combination of bespoke lifting equipment and minimal handling avoids post-rolling surface-related issues.

Technical support from our specialists

Our team of experienced metallurgists provide dedicated technical support to our customers, including selection of the most appropriate steel grade and size, detailed metallurgical analysis to solve specific processing problems, and the development of new and more advanced grades of steel for increasingly demanding applications.

Wire rod dimensions

Rod diameter	5.5 mm
Coil weight	1,800 - 2,200kg
Coil length	1,400 - 1,650mm
Coil dimensions	Outside diameter: 1,250mm max Inside diameter: 850mm min

Note: Standard tyre reinforcement wire rod dimensional tolerances:
Gauge +/-0.20mm, ovality 0.30mm max

Tyre reinforcement steel grades

The table below indicates the typical chemical analysis limits for British Steel's tyre reinforcement grades. Other grades and analysis limits can be considered upon request. Typical tensile strengths and reduction of area are displayed, however these can be tailored through process route optimisation.

Steel grade

Grade	C	Si	Mn	P	S	N	Cr	Tensile (MPa)	Reduction of area (%)
62C	0.62 – 0.65	0.19 – 0.22	0.48 – 0.53	≤0.011	≤0.011	≤0.006	–	920	≥46
72C	0.71 – 0.75	0.19 – 0.22	0.48 – 0.52	≤0.014	≤0.009	≤0.006	–	1030	≥40
84C	0.81 – 0.84	0.19 – 0.22	0.48 – 0.51	≤0.013	≤0.012	≤0.006	–	1120	≥37
95C+Cr	0.90 – 0.95	0.19 – 0.22	0.33 – 0.37	≤0.014	≤0.009	≤0.006	0.20 – 0.24	1260	≥37

BRITISHSTEEL.CO.UK/WIRE-ROD

A | PO Box 1, Brigg Road, Scunthorpe, North Lincolnshire, DN16 1BP
T | 44 (0)1724 402582 E | wirerod@britishsteel.co.uk

WRTCD:ENG:072025

Care has been taken to ensure that the contents of this publication are accurate, but British Steel Limited and its subsidiaries and associated undertakings (having the meaning set out in the Companies Act 2006) do not accept responsibility or liability for errors or information that is found to be misleading.

Copyright British Steel 2025

British Steel Limited is registered in England under number 12303256 with registered office at Administration Building, Brigg Road, Scunthorpe, DN16 1XA.

